

Kasmer

Kasmer Marble Industry & Trade Inc
Kasmer Mermer San. Tic. Ltd. Şti.

*Naturel
Beauty*



Hakkımızda

Yıllar boyu blok mermer sektöründe tecrübe kazanmış Kasmer Mermer End. Tic. San. Şti. uzmanlaşmış kadrosuyla blok mermer üreten ve pazarlayan şirketler arasında kendisine önemli bir yer edinmiştir. Mermer ocaklarımızda piyasada en çok rağbet gören gri mermer başta olmak üzere farklı renk gruplarında mermer üretmekteyiz. Ürettiğimiz mermerlerin büyük bir kısmını dış piyasaya sunmaktayız, bunun yanısıra geniş bir yurtiçi müşteri portföyüne sahibiz.

Yıllık mermer üretim kapasitemiz 40.000 ton civarındadır. Ana mermer ocağımız Azdavay'da olup ocağımız 600 hektarlık bir alanda yer almaktadır. Durmaksızın devam eden yeni mermer ocakları araştırma ve keşif çalışmalarımızda üretmiş olduğumuz mermerlerin dışında farklı mermerler üretmeyi hedeflemekteyiz.

About Us

Over the years, "Kasmer Marble Industry And Trade Ltd Company" has gained experience in Marble Sector by producing and trading marble blocks, with this way, find itself a prominent place among the companies in this sector..

In our quarries including the most popular marble, Maroon Marinace(Sicili Grey) we produce different colour groups which are Olive Avangard and Beige. The large portion of our produced marbles are offered to foreign markets, in addition to that we have built a large domestic customer network.

Our annual production capacity is approximately 40,000 tons. Our main quarry is located in an area of 600 hectares in Azdavay. With ongoing new field researches and discoveries, we targeted to produce new colour group of marbles.

Misyonumuz

Üretim kapasitemizi maksimum seviyede kullanarak sektörün en seçkin firmalarından biri olmayı misyonumuz olarak benimsedik. Temel prensibimiz doğal dokuya zarar vermeden, üretmiş olduğumuz mermer bloklarını müşteri memnuniyetine verimli ve etkin bir şekilde sunmak.

Vizyonumuz

Sektöründe başarısıyla, güvenilirliğiyle, girişimciliğiyle ve saygınlığıyla tanınmak ve daima bu değerleri korumak...



Our Mission

We have adopted as a mission to be one of the most distinguished company in the sector by maximized way of using our block marble production capacity that we have. Our main principle is, without harming to natural tissue, offer our produced marble blocks to our customers' satisfaction in an efficient and effective manner.

Our Vision

Known with its success, reliability, entrepreneurship and respect in the sector which operates and always preserve these values...





Hardness	Mohs	3-3,5
Unit Volume Weight (Dry)	(gr/cm ³)	2.701 ±0,054
Unit Volume Weight (Saturated)	gr/cm ³)	2.704±0,001
Porosity	(%)	0,298±0,101
Woit Ratio	(%)	0,298±0,101
Water Absorption	(%)	0,110±0,008
Weight Loss After Freezing	(%)	0,081±0,008
Uniaxial Compressive Strength	(kg/cm ²)	1470±50
Uniaxial Compressive Strength	(kg/cm ²)	1413±0,50
After Freezing and Thawing	(kg/cm ²)	1413±0,50
Bending Tensile Strenght	(kg/cm ²)	114±16
Abrosion Strenght by Friction	(cm ³ / ⁵⁰ cm ²)	11,3±0,33
Impzct Strenght	(kgcm/cm ²)	10,28±2,9

QUARY ADRESS: AZDAVAY / KASTAMONU / TURKEY

www.kasmer.com.tr

MARON MARINACE





Hardness	Mohs	3-3,5
Unit Volume Weight (Dry)	(gr/cm ³)	2,701 ±0,054
Unit Volume Weight (Saturated)	gr/cm ³)	2,704±0,001
Porosity	(%)	0,298±0,101
Woit Ratio	(%)	0,298±0,101
Water Absorption	(%)	0,110±0,008
Weight Loss After Freezing	(%)	0,081±0,008
Uniaxial Compressive Strength	(kg/cm ²)	1470±50
Uniaxial Compressive Strength	(kg/cm ²)	1413±0,50
After Freezing and Thawing	(kg/cm ²)	1413±0,50
Bending Tensile Strenght	(kg/cm ²)	114±16
Abrosion Strenght by Friction	(cm ³ / ⁵⁰ cm ²)	11,3±0,33
Impact Strenght	(kgcm/cm ²)	10,28±2,9

QUARY ADRESS: EFLANI / KARABÜK / TURKEY

www.kasmer.com.tr

KASMER GRAY






Hardness	Mohs	3-3,5
Unit Volume Weight (Dry)	(gr/cm ³)	2.701±0,054
Unit Volume Weight (Saturated)	gr/cm ³)	2.704±0,001
Porosity	(%)	0,298±0,101
Woit Ratio	(%)	0,299±0,101
Water Absorption	(%)	0,110±0,008
Weight Loss After Freezing	(%)	0,81±0,008
Uniaxial Compressive Strength	(kg/cm ²)	1470±50
Uniaxial Compressive Strength	(kg/cm ²)	1413±0,50
After Freezing and Thawing	(kg/cm ²)	1413±0,50
Bending Tensile Strenght	(kg/cm ²)	114±16
Abrosion Strenght by Friction	(cm ³ / ⁵⁰ cm ²)	11,3±0,33
Impact Strenght	(kgcm/cm ²)	10,28±2,9

QUARY ADRESS: AZDAVAY / KASTAMONU / TURKEY

www.kasmer.com.tr

OLIVE AVANGARDE





Hardness	Mohs	3,0
Unit Volume Weight (Dry)	(gr/cm ³)	2,679-2,706
Unit Volume Weight (Saturated)	(gr/cm ³)	2,681-2,708
Apparent Porosity	(%)	0,216-0,567
Water Absorption at atmospheric pressure	(%)	0,080-0,215
Absorption by volume	(%)	0,216-0,567
Total Porosity	(%)	0,346-0,736
Compacity	(%)	99,26-99,65
Water Absorption coefficient by capillarity	(gr/m ² .s0,5)	NPD*
Vertical abrasion resistance	(mm)	14,51-16,04
Reaction to fire (According to 96/601/EC)	Class	-
Uniaxial Compressive Strength (Dry Condition)	MPa	54,20-97,52
Uniaxial Compressive Strength (Dry Saturated)	MPa	49,29-93,06
Flexural strength under concentrated load	MPa	10,27-13,43
Flexural strength under constant moment	MPa	9,83-12,64

QUARY ADRESS: PINARBAŞI / KASTAMONU / TURKEY

www.kasmer.com.tr

CREMA LEMA









Hardness	Mohs	3,0
Unit Volume Weight (Dry)	(gr/cm ³)	2,679-2,706
Unit Volume Weight (Saturated)	(gr/cm ³)	2,681-2,708
Apparent Porosity	(%)	0,216-0,567
Water Absorption at atmosphric pressure	(%)	0,080-0,215
Absorption by volume	(%)	0,216-0,567
Total Porosity	(%)	0,346-0,736
Compasity	(%)	99,26-99,65
Water Absorption coefficient by capillarity	(gr/m ² .s0,5)	NPD*
Vertical abrasion resistance	(mm)	14,51-16,04
Reaction to fire (According to 96/601/EC)	Class	-
Uniaxial Compressive Strength (Dry Condition)	MPa	54,20-97,52
Uniaxial Compressive Strength (Dry Saturated)	MPa	49,29-93,06
Flexural strength under concentrated load	MPa	10,27-13,43
Flexural strength under constant moment	MPa	9,83-12,64

QUARY ADRESS: PINARBAŞI / KASTAMONU / TURKEY

www.kasmer.com.tr

CREMA LEMA (DARK)





Kasmer
Kasmer Marble Industry & Trade Inc
Kasmer Mermer San. Tic. Ltd. Şti.

Kasmer Mermer San. ve Tic. Ltd. Şti.
Seydiler OSB Yıbo Cd. No:9 Seydiler / TURKEY
Tel: +90 366 222 23 24 info@kasmer.com.tr



www.kasmer.com.tr